Characteristics	Test	Colorcoat® Interieurcoating	Colorcoat® Polyester	Colorcoat® PVDF	Colorcoat® SDP 35 (Armatec®)	Colorcoat Prisma®	Colorcoat HPS200® Ultra
Nominal total dry film thickness in µm	EN 13523-1	15	25	25	35	50	200
Gloss (60°)	EN 13523-2	25 – 40%	25 – 40%	25 – 40%	30 – 50%	30 – 40%	20 – 40%
Flexibility T-Bend test without cracking (16ºC)	EN 13523-7	4-5T	3T	2T	1T	0,5T	0T
Corrosion resistance[1]		4	3	3	2/3	1	1
Max. continuous operating temperature 24/7		90°C	90°C	100°C	90°C	120°	60°
Pencil hardness[1]		4	3	3	2	2	1
UV resistance[1]		4	3	1	2	1	1
Chemical resistance anorganic/organic[1 2]		3/3	2/2-3	1/2	2/2	1/1	1/2
Max. guarantee period wall (years) [3]		-	5	10	10	25	40
Max. guarantee period roof (years) [3]		-	-	-	10	20	40 [4]

[1] 1 = excellent, 2 = good, 3 = sufficient, 4 = acceptable
[2] Can strongly deviate for specific chemicals
[3] Maximum guarantee period is for inland. Coast area (< 1 km) on request.
[4] Maximum guarantee period depends on colour group.